

KÖSTER Technical guideline / Article number Issued: 01st of June 2008 Draft of translation BD 73 Flex Tape Wall Sleeve

11.034

Elastic formed part for permanent waterproofing of pipe penetrations in combination with waterproofing systems under ceramic coverings

Features

The KÖSTER BD 73 Flex Tape Wall Sleeve is made of NBR rubber with a mesh embedded in the middle. It is designed for long lasting and permanently elastic waterproofing. The combination of materials ensures a good bond with all waterproofing materials which are used under tile such as polymer dispersions and flexible mineral sealing slurries as well as waterproofing made of reaction resins.

layer of KÖSTER BD 50 dry completely. Then apply the second layer of KÖSTER BD 50. Integrate the wall sleeve completely into the waterproofing system through the application of the second layer of KÖSTER BD 50 over the overlaying mesh.

Clean tools and spots soiled with KÖSTER BD 50 immediately

Technical data

Colour grey Thickness 0.6 mm Resistance to temperature -20 °C to +90 °C Size $120 \text{ mm} \times 120 \text{ mm}$

Packaging

Cleaning of tools

after use with water.

Packages of 20 pieces

Field of application

The KÖSTER BD 73 Flex Tape Wall Sleeve is a system component for the permanent waterproofing of pipe penetrations in wall areas, e. g. penetrations for faucets, under ceramic coverings.

Storage

Store the material in a cool and dry place; in originally sealed packages, the material can be stored for 12 month.

Substrate preparation

The substrate must be sound and solid, dry and free of dust and grease. Loose, adhesion inhibiting parts and ridges must be removed.

Note for subsequent works

KÖSTER BD 73 Flex Tape Wall Sleeve is compatible with silicone, it will not bleeding through. KÖSTER BD 20 Flexible Tile Adhesive can be applied directly onto the floor sleeve.

Application

Prime the substrate with KÖSTER BD 50 Primer. Wait min. 3 hours. Then brush on the first layer of KÖSTER BD 50. Pull the KÖSTER BD 73 Flex Tape Wall Sleeve over the pipe penetration, place it into the fresh coating and press it on. Now, let the first

Technical guidelines cited

 KÖSTER BD 50 Primer
 Art.-No.
 7.091

 KÖSTER BD 50
 Art.-No.
 7.09

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.